

| Code | Description | Size | Colour |
|-------|-------------------|--------|--------|
| 12102 | Accent Gap Filler | 300 ml | White |

1. Description

Accent Gap Filler is a high-quality, plasto-elastic one component joint sealant based on acrylic dispersions.

2. Characteristics

- Very easy to apply
- Colourfast and waterproof after curing
- Can be painted over after curing
- Very good adhesion on many porous surfaces and aluminium.

3. Technical Data

| | |
|--|----------------------------------|
| Basis: | Acrylic Dispersion (Water Based) |
| Consistency: | Paste |
| Curing System: | Physical Drying |
| Skin Formation: (*) (23°C/50% R.H.) | Ca. 20 min. |
| Density: (**) | Ca. 1.67 g/ml |
| Maximum Allowed Distortion: | 10% |
| Application Temperature: | + 5°C → + 30°C |
| Service Temperature: (**) | -20°C → + 80°C |
| Shrinkage: (DIN 53451) | Ca. 15% . |

* This varies according to ambient conditions such as temperature, humidity, substrate etc

** This information applies to fully cured product

4. Applications

- Joints on window sills, between plinths & walls, between masonry etc
- Joints with movement less than 10%

5. Shelf Life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C. Protect from frosts.

6. Application Instructions

Surfaces: On most porous surfaces and on Aluminium.
State of Surface: Clean, dry and free of dust and grease.
Preparation: On highly Porous surfaces these should be primed with "diluted" Accent Gap Filler (1 part Accent Gap Filler & 2 parts Water).

Soudal recommends a preliminary compatibility test to ensure that the user is satisfied with the result given.

Joint Size:

| | |
|---------------------------|--|
| Minimum Width for Joints: | 1mm |
| Maximum Width for Joints: | 10mm |
| Minimum Depth for Joints: | 5mm |
| Recommendation: | depth = width Avoid 3 point adhesion in larger joints |

Application

| | |
|--------------------------|---|
| Method: | With manual or pneumatic caulking gun. Finish with a spatula or putty knife. Do not apply when rain or frost is imminent during curing process |
| Application temperature: | +5°C to +35°C |
| Clean Up after use | Uncured: Accent Gap Filler can be removed with water from tools, tiles and other surfaces immediately |
| Repair: | Cured: To be removed mechanically only with Accent Gap Filler |

7. Limitations

- There is no adhesion to the following types of substrates of PE, PP, PTFE (Teflon) and Bituminous substrates.
- Do not use in applications where continuous water immersion is possible
- The paint applied must be sufficiently elastic to allow application on a plasto-elastic sealant
- Given the great diversity in available paints it is recommended to do a compatibility test prior to application.

8. Health and Safety Recommendation

- Apply the usual industrial hygiene.
- Please refer to MSDS for more detailed information

Remark

*The directives and data contained in this documentation is provided in good faith and accurately reflect Soudal's knowledge when its products are properly stored, handled and applied under normal conditions in accordance with Soudal's recommendations. In practice, the diversity of the materials, substrates, environments, site conditions, product storage, handling and application are such that no warranty can be given in respect to the merchantability or fit for purpose, of any product. All users must determine the product suitability for their purposes through testing. This technical data sheet and product properties may change without notice so users, suppliers and retailers of Soudal products should always check that the data sheets they have are the latest. To the maximum extent permitted by law, Soudal disclaims all warranties in relation to either the manufacture, storage and end use of the product. All orders are accepted subject to our current terms of trade. **If any clarification is required, please contact Soudal Technical Services or email info@soudal.co.nz.***

Last Updated: 31 July 2019

| | | |
|---------------------------|-----------------|---|
| Supplier contact details: | Soudal Ltd | Freephone: 0800 70 10 80 |
| | 14 Avalon Drive | Phone: (07) 847 5540 |
| | Nawton | Fax: (07) 847 0324 |
| | Hamilton 3200 | Email: info@soudal.co.nz |
| | New Zealand | Website: www.soudal.co.nz |